

PREPMax™

Timber Clean & Prep

Water based concentrated exterior timber cleaner. Cleans and treats, mould, mildew and other contaminants. Also assists penetration of the coating.

For use on all new, weathered, greyed and mould affected decking and other timber surfaces for a more aggressive preparation prior to staining or coating.

KEY FEATURES:

- Clean and brightens
- Treats mould
- Assists in opening the fibres to aid penetration of the timber surface prior to coating

UNIQUE SELLING POINTS:

- Supplied as a concentrate – 1 litre makes 5 litre and 4 litres makes 20 litres
- Supplied in eco containers



APPLICATION TOOLS



Exclusive to Mitre 10

PREPMAX™



BEFORE



AFTER

COMMON QUESTIONS:

Q: Any special precaution we need to take before using?

A: Always use/wear personal protective equipment and avoid contact with vegetation, painted or metal surfaces (corrosive properties may react with metal) but if contact does occur, rinse immediately and thoroughly with water. It is a good idea to keep all surrounding areas well saturated with water during the cleaning process to dilute the rinsing off water.

APPLICATION:

- Sweep and wash down with water to remove any surface dirt.
- Shake PREPMAX concentrate thoroughly. Mix 1 part PREPMAX to 4 parts water in a plastic container.
- Use water to wet the timber area to be cleaned.
- Using a stiff bristle broom/brush apply the PREPMAX mixture generously to the timber surface in sections, ideally along the full length of each piece of timber. Scrub the timber vigorously to ensure good “foaming” of the mixture. Avoid spot cleaning as it may create an uneven finish.
- Leave the mixture on the timber surface for approximately 15 min. During this time, it may be necessary to apply more mixture to ensure the surface is kept wet. Avoid applying to hot surfaces and in direct sunlight.
- Rinse off the timber surface thoroughly using a low-medium pressure wash down. Note: Failure to remove the solution could result in an uneven finish of the coating.
- Allow the timber surface to dry before applying the coating.

For severe staining, tannin rich or badly weathered and greyed timber a stronger mixture or repeat applications may be required